

TECHNICAL SPECIFICATION



Index 55005EURO7 -2924

Fabric Glass fabric, 205±15 g/m², white color

Coating Two-side CR

80 g/m² for each side, unvulcanized

Available colors Blac

Spacer Embossed LDPE foil

Parameters	Unit	Value	Test methods
Useful width	cm	≥ 124	PN-EN ISO 2286-1
Weight	g/m²	365±30	PN-EN ISO 2286-2

Storage conditions

Unvulcanized coated fabric should be stored in dry rooms, in conditions that protect against getting wet, dirty, mechanical and chemical damage. The storage temperature should be between +10 and +30°C. Away from sources of heat, direct UV radiation and ionizing radiation that generates ozone (e.g. operating electric engines). Unvulcanized fabrics should be stored unstressed, wound on a roller and wrapped in stretch foil. The rollers can be stacked in a maximum of 3 layers. The maximum shelf life of the product is 90 days from the production date.

(7:00-15:00)

COORDINATOR PAULINA WICHROWSKA

Specialty sales department

EXPORT MANAGER JOANNA PIECHOCKA

Export sales department

Tel: +48 566 994 008 pwichrowska@lubawa.com.pl mobile: +48 607 140 930 jpiechocka@lubawa.com.pl

Dokumentacja jest własnością firmy Lubawa SA Ostrów Wielkopolski. Podlega ochronie prawnej wynikającej z prawa autorskiego. Wszelkie wykorzystywanie bez pisemnej zgody właściciela jest niedozwolone.

LUBAWA S.A. ul. Staroprzygodzka 117, 63-400 Ostrów Wielkopolski

+48 62 737 5777

Department of sales of fabrics,

rubbers, rescue and safety

akoseda@lubawa.com.pl

COORDINATOR

ANNA KOSEDA

equipment Tel.: + +48 603 201 773









































