

## CONDUCTIVE BLACK TAPE NTU-46

<b>Index</b>	55005NTU461-0759
<b>Fabric</b>	Polyamide 100%, 90-100g/m <sup>2</sup> , color black with white print SEMI CONDUCTING TAPE---REMOVE WHEN SPLICING OR TERMINATING
<b>Coating</b>	One-side, SBR, 40-60g/m <sup>2</sup> , vulcanized
<b>Available colours</b>	Black

Physical parameters	Unit	Value	Test standard
Resistivity	Ω x cm	< 100	Internal Procedure/LUBAWA/1
Weight	g/m <sup>2</sup>	140 ± 25	PN-EN ISO 2286-2
Thickness	mm	≤ 0,25	PN-EN ISO 2286-3
Tensile strength warp	daN/5 cm	≥ 45	PN- EN ISO 1421
weft		≥ 30	
Aging test 90°C/24 h Tensile strength warp	daN/5 cm	≥ 45	PN- EN ISO 1421
weft		≥ 30	

possibility of cutting to a width of 20 mm

### Storage conditions

Coated vulcanized fabric should be stored in dry rooms, in conditions that protect against getting wet, dirty, mechanical and chemical damage. The storage temperature should be from -10 to +50°C. Away from direct sources of heat, UV radiation and ionizing radiation that generates ozone (e.g. operating electric motors). Fabrics should be stored taut, wound on a roller and protected with stretch foil. The rollers can be stacked with a maximum of 4 layers. The maximum shelf life of the product is 3 years from the date of production.

### Customer service (7:00-15:00)

COORDINATOR  
ANNA KOSEDA  
**Department of sales of fabrics,  
rubbers, rescue and safety  
equipment**  
Tel.: + 48 603 201 773  
akoseda@lubawa.com.pl

COORDINATOR  
PAULINA WICHROWSKA  
**Specialty sales department**  
Tel: +48 566 994 008  
pwichrowska@lubawa.com.pl

EXPORT MENAGER  
JOANNA PIECHOCKA  
**Export sales department**  
mobile: +48 607 140 930  
jpiechocka@lubawa.com.pl

Dokumentacja jest własnością firmy Lubawa SA Ostrów Wielkopolski. Podlega ochronie prawnej wynikającej z prawa autorskiego. Wszelkie wykorzystywanie bez pisemnej zgody właściciela jest niedozwolone.

