

TECHNICAL SPECIFICATION

CONDUCTIVE BLACK TAPE NTU-50

Index	55005NTU501-0759		
Fabric	Polyester 55 g/m2		
Coating	Two-side, SBR 70-90 g/m², wulkanizowana		
Available colours	Black		

Physical parameters	Unit	Value	Test standard
Resistivity	Ωxcm	< 100	Internal Procedure/LUBAWA/1
Weight	g/m2	130 ± 25	PN-EN ISO 2286-2
Thickness	mm	≤ 0,25	PN-EN ISO 2286-3

possibility of cutting to a width of 20 mm

Storage conditions

Coated vulcanized fabric should be stored in dry rooms, in conditions that protect against getting wet, dirty, mechanical and chemical damage. The storage temperature should be from -10 to +50°C. Away from direct sources of heat, UV radiation and ionizing radiation that generates ozone (e.g. operating electric motors). Fabrics should be stored taut, wound on a roller and protected with stretch foil. The rollers can be stacked with a maximum of 4 layers. The maximum shelf life of the product is 3 years from the date of production.

Customer service (7:00-15:00)


COORDINATOR PAULINA WICHROWSKA Specialty sales department

Tel: +48 566 994 008 pwichrowska@lubawa.com.pl EXPORT MENAGER JOANNA PIECHOCKA **Export sales department**

mobile: +48 607 140 930 jpiechocka@lubawa.com.pl

Dokumentacja jest własnością firmy Lubawa SA Ostrów Wielkopolski. Podlega ochronie prawnej wynikającej z prawa autorskiego. Wszelkie wykorzystywanie bez pisemnej zgody właściciela jest niedozwolone.

LUBAWA S.A. ul. Staroprzygodzka 117, 63-400 Ostrów Wielkopolski



akoseda@lubawa.com.pl

Department of sales of fabrics,

rubbers, rescue and safety

COORDINATOR

ANNA KOSEDA

equipment Tel.: + +48 603 201 773

+48 62 737 5708



